productinformation

tesa® 4957

Double-sided general purpose PE-foam tape

tesa® 4957 is a double-sided tape consisting of a very conformable closed cell PE-foam backing and a shear resistant modified acrylic adhesive. It is suitable for outdoor use and available in both black and white.

tesa® 4957 features:

- High immediate bond on rough surfaces
- Very good compensation for design tolerances
- Leveling out of different thermal expansion of materials
- Shock absorption and sealing function

Main Application

- POS displays, exhibition sample displays
- Shelf edge labels
- Cable channels, window and kitchen profiles
- Decorative glass or mirror elements on furniture
- Signs and Emblems

Technical Data

	Backing material	PE foam	Type of adhesive	tackified acrylic
	Color	black/white	Elongation at break	200 %
•	Total thickness	1100 μm	Tensile strength	6 N/cm

Adhesion to

•	Steel (initial)	4.0 N/cm	•	Steel (after 14 days)	4.0 N/cm
•	ABS (initial)	4.0 N/cm	•	ABS (after 14 days)	4.0 N/cm
•	Aluminium (initial)	4.0 N/cm	•	Aluminium (after 14 days)	4.0 N/cm
•	PC (initial)	4.0 N/cm	•	PC (after 14 days)	4.0 N/cm
•	PE (initial)	1.7 N/cm	•	PE (after 14 days)	2.2 N/cm
•	PET (initial)	4.0 N/cm	•	PET (after 14 days)	4.0 N/cm
•	PP (initial)	1.8 N/cm	•	PP (after 14 days)	3.3 N/cm
•	PS (initial)	4.0 N/cm	•	PS (after 14 days)	4.0 N/cm
•	PVC (initial)	4.0 N/cm	•	PVC (after 14 days)	4.0 N/cm



tesa® 4957

Double-sided general purpose PE-foam tape

Properties

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance

- 80°C
- Resistance to chemicals
- Softener resistance
- Static shear resistance at 23°C
- Static shear resistance at 40°C





Evaluation across relevant tesa® assortment: • • • • very good

good

• • medium

Additional Information

Liner variants:

PV0 brown glassine paper (70 μm)

PV4 white with tesa® logo PE-coated paper (122 μm)

PV6 blue PP (80 µm)

PV12 transparent PET (75µm)

PV15 blue PE (100 μm)

tesa® 4957 has been tested and approved by IFT institute for window bar mounting (IFT report number 509 30742/1).

tesa® 4957 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).

Peel Adhesion:

- immediately: foam splits on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splits on Steel, Aluminium, ABS, PC, PS, PET, PVC