# productinformation

## tesa® 51970 Transparent double-sided filmic tape

tesa® 51970 is a transparent double-sided tape consisting of a PP-film backing and a tackified adhesive.

tesa<sup>®</sup> 51970 features:

- Excellent combination of high tack and adhesion ÷.
- Secure bond even on materials such as PP and PE and rough surfaces
- Good temperature resistance and outdoor suitability

#### Main Application

- Mounting of plastic and wooden trims
- Mounting of decorative materials and displays
- Mounting of transparent signs and scales

#### **Technical Data**

| <ul> <li>Backing material</li> <li>Color</li> <li>Total thickness</li> <li>Type of adhesive</li> <li>Elongation at break</li> </ul>                                                                                           | PP film<br>transparent<br>220 μm<br>tackified acrylic<br>150 %                                                 | <ul> <li>Tensile strength</li> <li>Type of liner</li> <li>Colour of liner</li> <li>Thickness of liner</li> </ul>                                                                                                                                                                                                 | 50 N/cm<br>glassine<br>brown<br>71 μm                                                                           |  |  |  |  |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------|--|--|--|--|
| Adhesion to                                                                                                                                                                                                                   |                                                                                                                |                                                                                                                                                                                                                                                                                                                  |                                                                                                                 |  |  |  |  |
| <ul> <li>Steel (initial)</li> <li>ABS (initial)</li> <li>Aluminium (initial)</li> <li>PC (initial)</li> <li>PE (initial)</li> <li>PET (initial)</li> <li>PP (initial)</li> <li>PS (initial)</li> <li>PVC (initial)</li> </ul> | 13.0 N/cm<br>11.3 N/cm<br>10.2 N/cm<br>12.3 N/cm<br>5.4 N/cm<br>9.9 N/cm<br>6.8 N/cm<br>11.8 N/cm<br>10.5 N/cm | <ul> <li>Steel (after 14 days)</li> <li>ABS (after 14 days)</li> <li>Aluminium (after 14 days)</li> <li>PC (after 14 days)</li> <li>PE (after 14 days)</li> <li>PET (after 14 days)</li> <li>PP (after 14 days)</li> <li>PS (after 14 days)</li> <li>PVC (after 14 days)</li> <li>PVC (after 14 days)</li> </ul> | 13.5 N/cm<br>14.4 N/cm<br>12.8 N/cm<br>15.0 N/cm<br>6.8 N/cm<br>12.5 N/cm<br>8.8 N/cm<br>13.4 N/cm<br>17.0 N/cm |  |  |  |  |

#### **Properties**

|    | Temperature resistance short term                    | 130 °C            | Resistance to chemicals                             |  |
|----|------------------------------------------------------|-------------------|-----------------------------------------------------|--|
|    | Temperature resistance long term                     | 80 °C             | Softener resistance                                 |  |
|    | Tack                                                 | •••               | <ul> <li>Static shear resistance at 23°C</li> </ul> |  |
|    | Ageing resistance (UV)                               | •••               | <ul> <li>Static shear resistance at 40°C</li> </ul> |  |
| •  | Humidity resistance                                  | ••••              |                                                     |  |
| E١ | aluation across relevant tesa <sup>®</sup> assortmen | t: •••• very good | ●●● good ●● medium ● low                            |  |

For latest information on this product please visit http://l.tesa.com/?ip=51970

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



<sup>2</sup>age 1 of 2 - as of 28/08/2018 -

ę

## tesa<sup>®</sup> 51970 Transparent double-sided filmic tape

### Additional Information

Liner variants: PV0 brown glassine paper (65 μm) PV1 white glassine paper (84 μm) PV2 white embossed PP (85 μm) PV6 red MOPP-film (80 μm)

A fingerlift version (extended liner), tesa<sup>®</sup> 61970, is also available.

For latest information on this product please visit <u>http://l.tesa.com/?ip=51970</u>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

